

A 57.40

Description

Anaerobic curing adhesive for the gasketing and sealing of flanges.

To replace solid gaskets, gives elastic cured films.

To seal against gases, water LPG, hydrocarbons, oils and other chemicals.

Thixotropic property prevents migration of the sealant before or during curing.

Shocks and vibrations resistances are unaffected properties of sealing in the range of temperature from -55 to +150°C.

Physical Properties

* Composition	anaerobic methacrylate
* Colour	: orange
* Fluorescence	: under blue light
* Viscosity (25°C - mPa.s)	: 30000 – 1200000 HT
* Specific weight (25°C - gr/ml)	: 1,1
* Max diameter of thread/gap filling	: 0,50 mm
* Flash point	: about 100°C
* Solvent content	: none
* Shelf life 25°C (T max <28°C)	: 1 years

Curing properties

Bolt M 10 x 20 – quality 8.8 – nut h = 0,8.d

* Handling cure time	: 15-30 minutes
* Functional cure time	: 3-6 hours
* Full cure time	: 6-24 hours
* Shear strength (ASTM D-1002)	: 5-10 N/mm ²
* Tensile strength (ASTM D-20959)	: 5-8 N/mm ²
* Impact strength (ASTM D-950)	: 5-10 N.mm/mm ²
* Temperature range	: -55+150°C

Handling and safety properties

Refer to Material Safety Data Sheet.

Suggestions, processing and use of our products correspond to the best knowledge at printing of this leaflet and are always given without obligation. You only can serve as a clue in consideration of the changing conditions; from this no liabilities, liability and guarantee claims can be derived. Own tests must be carried out before application. Every manufacturer of our products is liable for the retention everything legal to regulations.